



TRISEP® TS40

High Rejection Process

NF Membrane

TRISEP® TS40 membrane delivers value by purifying and separating solutes. TS40 has high rejection of divalent and polyvalent ions while allowing the majority of monovalent ions to pass through the membrane. With a molecular weight cut-off in the range of 200-300 Daltons, TS40 is a piperazine-based membrane that is often used to demineralize and concentrate organic solutes. TS40 membrane sheet is available in both dry and wet flat sheet rolls and is FDA compliant.

MEMBRANE CHARACTERISTICS

Membrane Chemistry	Backing Material	Stabilized MgSO ₄ Rejection (%) ^a	Minimum MgSO ₄ Rejection (%)
Thin-Film Polypiperazine	Non-Woven Polyester	99.0	98.5

Flux Range LMH (GFD) ^b	Thickness (µm)	pH Range	Chlorine Tolerance ^c
40.8 – 61.2 (24.0 – 36.0)	130 – 170	1.0 – 12.0	< 0.1 ppm

a Typical NaCl rejection: 40%

b Test conditions: 2,000 ppm MgSO₄, 7.6 bar (110 psi), 25°C (77°F), 15% recovery, pH 8.0, 30 minutes operation. Membrane specifications may change without notice as design revisions occur.

c Oxidizing agents, such as free chlorine, in contact with piperazine membranes may result in shortened operating life or membrane failure.

IMPORTANT INFORMATION

Standard Sizes: TRISEP flat sheet membrane is available in a sample size of 305 mm x 1,016 mm (12 in x 40 in) and in a nominal roll size of 305 m x 1,016 mm (1,000 ft x 40 in). Custom lengths may be available on request.

Initial Flush: MANN+HUMMEL Water & Fluid Solutions recommends flushing membrane for 30 minutes and discarding permeate during the flush prior to operation.

Storage: Membrane is shipped dry unless wet membrane is specifically requested. Membrane shipped dry should be stored in a cool, dry place. If shipped wet, TRISEP membrane must remain sealed and refrigerated prior to use. Please see Membrane Storage Guide – Flat Sheet Membrane (TSG-O-011).

Contact

Europe
 Germany: +49 611 962 6001
 Italy: +39 0721 1796201
 info@microdyn-nadir.com

Americas
 USA: +1 805 964 8003
 sales.mnus@microdyn-nadir.com

Asia
 Singapore: +65 6457 7533
 China: +86 10 8413 9860
 waterchina@mann-hummel.com